

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing
A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031
P.O Box 240, North Melbourne, Victoria 3051
Phone (03) 9371 2400

TEST REPORT

Client : Regupol (Australia) Pty Ltd
155 Smeaton Grange Road
Smeaton Grange NSW 2567

Test Number : 21-004895
Issue Date : 21/09/2021
Print Date : 23/09/2021
Order Number : PO0000817

Sample Description Clients Ref : "Everroll(R) Rubber Flooring, Intensity, Active,Shape"
Rubber flooring
End Use : Flooring
Nominal Composition : 100% EPDM Granules and PUR binder
Nominal Mass per Unit Area/Density : 5.51kg/m2
Nominal Thickness : 4mm

ISO 9239.1:2010 Part 1

Reaction to Fire Tests for Floorings. Determination of the Burning Behaviour using a Radiant Heat Source

Date of Sample Arrival 12-02-2018

Date Tested 27-02-2018

CHF Value	1	2	3	Mean	
Non Directional	3.6	3.6	3.0	3.4	kW/m ²
Smoke Value	1	2	3	Mean	
Non Directional	46	18	33	32	%.min

Blistering Yes
Penetration of flame through to substrate Yes

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test, they are not intended to be sole criterion for assessing the potential fire hazard of the product in use.

Sample was conditioned in accordance with BSEN 13238:2010 at a temperature of 23±2°C and relative humidity of 50±5% for a minimum of 48 hours prior to testing.

Each specimen was clamped as supplied by client prior to testing.

250059

54444

Page 1 of 1



Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.

