

**ISO 9239-1:2010 TESTING  
FOR  
TARKETT, INC  
ON  
INERTIA RUBBER TILE INRH LB4 ¼  
SKU: 400471082 RUN: 03.11.20  
VTEC #100-7010-3  
TESTED: DECEMBER 7, 2021**



# VTEC Laboratories Inc.

December 8, 2021

**Client:** Tarkett, Inc.  
1001 Rue Yamasaka East  
Farnham, Quebec, J2N 1J7  
Canada

**Attention:** Richard Bérubé

**SUBJECT:**

Standard Test Method for Determination of the Burning Behaviour Using a Radiant Heat Energy Source according to ISO 9239-1:2010 specifications.

**DISCLAIMER:**

This is a factual report of the results obtained from the laboratory test of sample products. The results may be applied only to the products tested and should not be construed as applicable to other similar products of the manufacturer. The report is not a recommendation or a disapprobation by VTEC Laboratories Inc., of the material tested. While this report may be used for obtaining product acceptance, it may not be used in advertising.

**NOTICE:** VTEC Laboratories Inc., will not be liable for any loss or damage resulting from the use of the data in this report, in excess of the invoice. This report pertains to the sample tested only. Such report shall not be interpreted to be a warranty, either expressed or implied as to the suitability or fitness of said sample for such uses or applications, as the party contracting for the report may apply such sample.

**Material Tested:**

- |                          |  |
|--------------------------|--|
| 1) Product Description:  | Inertia Rubber Tile INRH LB4 ¼<br>Sku: 400471082 Run: 03.11.20 |
| 2) Supplier:             | Tarkett, Inc   |
| 3) Specimen Composition: | Heterogeneous  |
| 4) Average Thickness:    | 0.25 in.   |
| 5) Color:                | White  |
| 6) Method of Mounting:   | Adhered onto Cement Board Backing                              |
| 7) Flux Profile Date:    | December 7, 2021   |

**Test Results:**

	<b>Sample #1</b>	<b>Sample #2</b>	<b>Sample #3</b>
1) Specimen preheat Time (mins)	2:00	2:00	2:00
2) Total Burn Length (cm)	5	9	10
3) Time to Maximum Burn Length (mins)	14:49	21:27	19:15
4) HF - 30 (kW/m <sup>2</sup> )	>11	>11	>11
5) CHF (kW/m <sup>2</sup> )	>11	>11	>11
6) Average HF-30 (kW/m <sup>2</sup> )	>11		
7) Standard Deviation	N/A		
8) Coefficient of Variation (%)	N/A		
9) Average CHF (kW/m <sup>2</sup> )	>11		
10) Standard Deviation	N/A		
11) Coefficient of Variation (%)	N/A		
12) Maximum Optical Attenuation (%)	19.41%	28.85%	29.45%
13) Average Optical Attenuation (%)	25.90%		
14) Smoke Generation (%*min)	40.04	170.03	232.53
15) Average Smoke Generation (%*min)	147.53		

**Observations:** No premature ignition during the initial 2 minute heating period, no melting, delamination, or shrinking. Blistering occurred on samples 2 and 3 with popping.



Neil Schultz  
Executive Director



Amirudin Rahim  
Technical Director